

**MEXBLEND ECO PCP 80 H BK**

<b>Description</b>	PC/PP Contains recycled material, high flow, high impact and high surface tension.		
<b>Color</b>	Black	<b>Additional formulations</b>	
<b>Norm</b>	-	Fluidity form 1 to 50 gr/10'	EL - High impact
<b>Sector:</b>	Automotive, furniture, white	UV - Light stabilized	IB - Hybrid Mineral+GF
<b>Processing</b>	Injection	UL94 - Flame retardant	H - Heat stabilized

**Applications:** PC/PP is widely used in the automotive, electronics, aerospace and additive manufacturing sectors, standing out for its combination of high impact resistance, rigidity, thermal resistance and ease of processing.

<b>Mechanical Properties</b>	<b>Values</b>	<b>Unit</b>	<b>ISO</b>
Density	1.05	g/cm <sup>3</sup>	1183
Filler Content	-	%	3451
Melt Flow Index 260° C/5 kg	16	g/10min	1133
Shrinkage	0.4 - 0.6	%	294

<b>Mechanical Properties</b>	<b>Values</b>	<b>Unit</b>	<b>ISO</b>
Tensile strength at yield	55	MPa	527-1
Flexural Modulus	1500	MPa	178
IZOD Impact strength, notched (23° C)	22	KJ/m <sup>2</sup>	180 1eA
IZOD Impact strength, notched (-30° C)	7,0	KJ/m <sup>2</sup>	180 1eA

<b>Thermal Properties</b>	<b>Values</b>	<b>Unit</b>	<b>ISO</b>
HDT (0.45 MPa)	-	° C	75
HDT (01.82 MPa)	110	° C	75

<b>Flammability</b>	<b>Values</b>	<b>Unit</b>	<b>ISO</b>
Flame rating at 3.2 mm	HB	-	UL94

<b>Processing Conditions</b>	<b>Values</b>		
Drying	3h/90° C	Suggeste max moisture	0.15 %
Hopper	240° C	Min temperture	240 ° C
1 <sup>st</sup> Zone	250° C	Max temperture	275 ° C
2 <sup>nd</sup> Zone	250° C	Injection rate	Medium/High
3 <sup>rd</sup> Zone	260° C	Injection pressure	40 ÷ 80 MPa
Nozzle	265° C	Injection time	3 ÷ 15 Sec.
Moulds	50 - 70° C	Cooling time	20 ÷ 60 Sec.

Melt Temperature: A critical parameter, generally between 200-300° C for PP, with the recommendation to avoid exceeding 220° C for flame-retardant (FR) grades to prevent degradation.

Mold Temperature: Higher mold temperatures can improve part brilliance and appearance. A typical mold temperature for PP GF is around 20 ÷ 50° C.

Injection Speed: Use high injection speeds to ensure good surface finish and prevent weld lines.

Injection Pressure: Pressure should be high enough to fill the part effectively but not excessive, which can cause flashing or burning.

Mold Venting: Essential for preventing burn marks by allowing trapped gases to escape.

Fiber Length Control: The shear forces within the injection molding barrel can significantly reduce fiber length. Processing conditions need to be managed to control this.

After annealing treatment, PP products can eliminate residual internal stresses and improve impact resistance.

To reduce internal stress and deformation, high-speed injection should be chosen, but some PP grades and molds are not applicable.

The information and data contained herein is believed to be accurate and are given in good faith. However, accuracy is not guaranteed and no warranty nor representation in such regard or in connection with any of the products referred to herein is given and Mexpolimeros disclaims all liability accordingly, whether in contract tort or otherwise.