

**MEXPRENE PPH 8 GF25 H NC**

<b>Description</b>	Polypropylene homopolymer with 25% glass fiber reinforced, heat stabilized		
<b>Color</b>	Natural	<b>Additional formulations</b>	
<b>Norm</b>	-	Fluidity form 1 to 50 gr/10'	EL - High impact
<b>Sector:</b>	Automotive, furniture, white	UV - Light stabilized	IB - Hybrid Mineral+GF
<b>Processing</b>	Injection	UL94 - Flame	AB - Anti bacterial

**Applications:** Piezas exteriores, rejillas de radiador, manijas de puertas y componentes de motor parts. Piezas mecánicas de alta resistencia, componentes de carga y piezas de maquinaria.

Mechanical Properties	Values	Unit	ISO
Density	1.08	g/cm <sup>3</sup>	1183
Filler Content	25	%	3451
Melt Flow Index 230° C/2.16 kg	6	g/10min	1133
Melting Point (DSC)	167	° C	3146

Mechanical Properties	Values	Unit	ISO
Tensile strength at yield	78	MPa	527-1
Flexural Modulus	4800	MPa	178
IZOD Impact strength, notched (23° C)	-	lb-ft/in2	-
IZOD Impact strength, notched (23° C)	12,0	KJ/m <sup>2</sup>	180 1eA

Thermal Properties	Values	Unit	ISO
HDT method A (1.820 MPa)	146	° C	75-1

Flammability	Values	Unit	ISO
Flame rating at 3.2 mm	HB		UL94

Processing Conditions	Values	Unit	ISO
Drying	-	Suggeste max moisture	0.15 %
Hopper	220° C	Min temperture	200 ° C
1 <sup>st</sup> Zone	230° C	Max temperture	240 ° C
2 <sup>nd</sup> Zone	230° C	Injection rate	Medium/High
3 <sup>rd</sup> Zone	240° C	Injection pressure	40 ÷ 80 MPa
Nozzle	240° C	Injection time	3 ÷ 15 Sec.
Moulds	20 - 40° C	Cooling time	20 ÷ 60 Sec.

Melt Temperature: A critical parameter, generally between 200-300° C for PP, with the recommendation to avoid exceeding 220° C for flame-retardant (FR) grades to prevent degradation.

Mold Temperature: Higher mold temperatures can improve part brilliance and appearance. A typical mold temperature for PP GF is around 20 ÷ 50° C.

Injection Speed: Use high injection speeds to ensure good surface finish and prevent weld lines.

Injection Pressure: Pressure should be high enough to fill the part effectively but not excessive, which can cause flashing or burning.

Mold Venting: Essential for preventing burn marks by allowing trapped gases to escape.

Fiber Length Control: The shear forces within the injection molding barrel can significantly reduce fiber length. Processing conditions need to be managed to control this.

After annealing treatment, PP products can eliminate residual internal stresses and improve impact resistance.

To reduce internal stress and deformation, high-speed injection should be chosen, but some PP grades and molds are not applicable.

The information and data contained herein is believed to be accurate and are given in good faith. However, accuracy is not guaranteed and no warranty nor representation in such regard or in connection with any of the products referred to herein is given and PMexpolimeros disclaims all liability accordingly, whether in contract tort or otherwise.

